

10-17-00

A

UTILITY PATENT APPLICATION TRANSMITTAL

Attorney Docket No. 09792909-4652

First Named Inventor or Application Identifier

Kazuhiro Shimoda

Express Mail Label No: EL654783320US

Only for new nonprovisional applications under 37 CFR 1.53(b))

ADDRESS TO: Assistant Commissioner for Patents
Box Patent Application
Washington, DC 20231

APPLICATION ELEMENTS

See MPEP chapter 600 concerning utility patent application contents.

1. ☒ Specification Total Pages 27
2. ☒ Drawing(s) (35USC 113) Total Pages 15
3. ☒ Declaration and Power of Attorney Total Pages 4
- a. ☒ Unexecuted(original or copy)
- b. ☐ Copy from prior application (37CFR 1.63(d))
(for continuation/divisional with Box 14 completed)

[Note Box 4 Below]

i. ☐ DELETION OF INVENTOR(S)Signed statement attached deleting
inventor(s) named in the prior
application, see 37 CFR 1.63(d)(2) and 1.33(b).

4. ☒ Incorporation By Reference (usable if Box 3b is checked)
The entire disclosure of the prior application, from which
a copy of the oath or declaration is supplied under Box 3b,
is considered as being part of the disclosure of the
accompanying application and is hereby incorporated by
reference therein.

ACCOMPANYING APPLICATION PARTS

5. ☐ Assignment Papers (cover sheet & documentation)
6. ☒ Letter under 37 CFR 1.41(c).
7. ☐ English Translation Document (if applicable)
8. ☐ Information Disclosure Statement (IDS)/PTO-1449 ☐ Copies of IDS Citations
9. ☒ Preliminary Amendment
10. ☒ Return Receipt Postcard (MPEP 503)
(Should be specifically itemized)
11. ☐ Small Entity ☐ Statement filed in prior Application,
Statement(s) Status still proper and desired
12. ☒ Certified copy of Japanese priority document No. P11-294406 filed October 15, 1999

14. If a CONTINUING APPLICATION, check appropriate box and supply the requisite information:

☐ Continuation ☐ Divisional ☐ Continuation-in-part (CIP) ☐ of prior application No:

CLAIMS AS FILED

(1) FOR	(2) NUMBER FILED	(3) NUMBER EXTRA	(4) RATE	(5) BASIC FEE
TOTAL CLAIMS 20	8		18.00	0.00
INDEPENDENT CLAIMS 03	2		80.00	0.00
ANY MULTIPLE DEPENDENT CLAIMS?				0.00
<input type="checkbox"/> YES <input checked="" type="checkbox"/> NO			TOTAL FEE	\$710.00

☒ The Commissioner is hereby authorized to charge any additional fees which may be required in connection with this application, or credit any overpayment to ACCOUNT NO. 19-3140. A duplicate copy of this sheet is enclosed.

☒ A check in the amount of \$710.00, to cover the filing fee is enclosed.

15. CORRESPONDENCE ADDRESS: David R. Metzger
SONNENSCHN NATH & ROSENTHAL
P.O. Box #061080
Wacker Drive Station, Sears Tower
Chicago, IL 60606-1080
Customer ID #26263
Telephone (312) 876-8000 - Fax (312) 876-7934

SIGNATURE

David R. Metzger (Reg. No. 32,919)

DATE October 16, 2000

U-11

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

PRELIMINARY AMENDMENT ACCOMPANYING APPLICATION

APPLICANT: Kazuhito Shimoda, et al. ATTY. DOCKET NO. 09792909-4652

SERIAL NO.

DATE FILED:

INVENTION: "APPARATUS AND METHOD FOR PRODUCING OPTICAL
COMPONENT"

Assistant Commissioner of Patents
Washington, D.C. 20231


S I R:

Between the title and the heading "Background of the Invention" on page 1, insert the
following:

--RELATED APPLICATION DATA

The present application claims priority to Japanese Applications No. P11-294406 filed
October 15, 1999, which application is incorporated herein by reference to the extent
permitted by law.

Respectfully submitted,

 (Reg. No. 32,919)
David R. Metzger
SONNENSCHN NATH & ROSENTHAL
P.O. Box #061080
Wacker Drive Station
Sears Tower
Chicago, IL 60606-1080
Customer #26263

Attorneys for Applicant(s)

APPARATUS AND METHOD FOR PRODUCING OPTICAL COMPONENT

BACKGROUND OF THE INVENTION

The present invention relates to an apparatus and a method for producing an optical component by forming a multi-layer film on a base.

To realize good optical characteristics of an optical component comprised of an optical film, such as a dichroic mirror, the optical film is required to be of a multi-layer structure having at least ten optical thin layers. The optical thin layer is formed by a low refractive index material such as MgF_2 or SiO_2 or a high refractive index material such as TiO_2 or Nb_2O_5 . A usual batch process used for producing an optical component comprised of an optical film having a multi-layer structure of optical thin layers involves evaporating raw materials for the optical thin layers in a vacuum system in accordance with a vapor-deposition process or sputtering process, to form the optical thin layers on a transparent member such as a glass board.

One example of a related art method of producing an optical component by forming an optical film having a multi-layer structure of optical thin layers has been disclosed in Japanese Patent Laid-open No. Hei 11-119002.

In accordance with this method, optical thin layers are continuously formed on a base, typically, a film in such a manner that the configuration of the optical thin layers is adjusted to a predetermined optically designed configuration as a whole, by forming the optical thin layers on the base, and simultaneously controlling a thickness of each layer to satisfy a specific light transmission characteristic by using, for example, an optical monitor.

The method disclosed in the above document, Japanese Patent Laid-open No. Hei 11-119002, however, has the following problems: namely, since the method fails in means for accurately measuring a thickness of each of optical thin layers continuously formed on the base such as film, the thickness of the optical thin layer intended to be adjustably formed is, really, inaccurately measured. This gives rise to not only a problem that the optical component produced by this method cannot exhibit ideal optical characteristics due to a deviation of the thickness of each optical thin layer from the ideal thickness, but also a problem that a variation in optical characteristics occurs between optical components produced by this method.

For example, as shown in Fig. 14, when each optical

thin layer is formed at a usual formation rate in accordance with the related art method, an optical characteristic represented by a light transmittance is largely changed due to a change in thickness of the optical thin layer. In the figure, values "74.76 nm", "94.76 nm", and "114.76 nm" designate the thicknesses of the optical thin layers. Even when each optical thin layer is formed at a formation rate slower than the usual rate in accordance with the related art method, as shown in Fig. 15, an optical characteristic represented by a light transmittance is largely changed due to a change in thickness of the optical thin layer. In the figure, values "0 nm", "65.5 nm", "97.3 nm" and "112.4 nm" designate the thicknesses of the optical thin layers.

The above related art method has a further problem that since the film thickness adjustment is performed for each of optical thin layers constituting an optical film, it takes a lot of time to form the optical film composed of the optical thin layers.

SUMMARY OF THE INVENTION

An object of the present invention is to provide an apparatus and a method for producing an optical component, each of which is capable of easily, stably producing an

optical component having good optical characteristics.

To achieve the above object, according to a first aspect of the present invention, there is provided an optical component producing apparatus for forming a multi-layer film, which is composed of alternately stacked layers different in optical characteristic, on a base, the apparatus including: film formation means for forming the multi-layer film on the base; measurement means for measuring an optical characteristic of the optical component obtained by forming the multi-layer film on the base; and control means for controlling a thickness of a portion of the multi-layer film formed by the film formation means on the basis of the measured optical characteristic of the optical component.

According to a second aspect of the present invention, there is provided an optical component producing method for forming a multi-layer film, which is composed of alternately stacked layers different in optical characteristic, on a base, the method including: measuring an optical characteristic of the optical component obtained by forming the multi-layer film on the base; and controlling, on the basis of the measured optical characteristic of the optical component, a thickness of a portion of the multi-layer film to be

formed on the base.

With these configurations, layers of a multi-layer film are formed one by one on the base (by the film formation means), wherein an optical characteristic of an optical component obtained by forming the multi-layer film on the base is measured (by the measurement means), and a portion of the multi-layer film formed by the film formation means is controlled (by the control means) on the basis of the measured optical characteristic of the optical component. Here, by selecting a portion exerting the largest effect on the optical characteristic of the optical component as the above portion of the multi-layer film, the optical component having a good optical characteristic can be formed. Further, since the thickness of only a portion of the multi-layer film is measured, the film thickness control can be easily performed. As a result, it is possible not only to produce an optical component having a good optical characteristic but also to produce a plurality of optical components without a variation in optical characteristic therebetween.

In the apparatus according to the first aspect of the present invention, preferably, the measurement means measures a transmittance of the optical component, and

the control means terminates the film formation by the film formation means at the portion of the multi-layer film when the measured transmittance of the optical component is changed to be decreased.

In the method according to the second aspect of the present invention, preferably, the measurement step includes the step of measuring a transmittance of the optical component; and the control step includes the step of terminating the film formation at the portion of the multi-layer film when the measured transmittance of the optical component is changed to be decreased.

With these configurations, the transmittance of the optical component is measured (by the measurement means), and the film formation (by the film formation means) at the portion of the multi-layer film is terminated when the measured transmittance of the optical component is changed to be decreased. As a result, an optical component, which is composed of the multi-layer film exhibiting a good optical characteristic formed on the base, can be obtained.

The above preferable apparatus, specifying the transmittance as the optical characteristic, according to the first aspect of the present invention, may further include removal means for removing the layer portion

formed during a period of time from a time point when the increase/decrease of the measured transmittance of the optical component is stopped to a time point when the measured transmittance is changed to be decreased.

The above preferable method, specifying the transmittance as the optical characteristic, according to the second aspect of the present invention, may further include removal step of removing a layer portion formed during a period of time from a time point when the increase/decrease of the measured mean light transmittance of the optical component is stopped to a time point when the measured mean light transmittance is changed to be decreased.

With these configurations, since a layer portion formed during a period of time from a time point when the increase/decrease of the measured transmittance of the optical component (by the measurement) is stopped to a time point when the measured transmittance is changed to be decreased is removed (by the removal means), the layer thickness can be finely adjusted. As a result, it is possible to produce an optical component capable of more accurately exhibiting a good optical characteristic.

In the apparatus according to the first aspect of the present invention, preferably, the control means

controls a thickness of one layer of the plurality of alternately stacked layers, the one layer having a higher refractive index and being positioned near the uppermost surface remotest from the base.

In the method according to the second aspect of the present invention, preferably, the control steps includes the step of controlling a thickness of one layer of the plurality of alternately stacked layers, the one layer having a higher refractive index and being positioned near the uppermost surface remotest from the base.

With these configurations, a thickness of one layer of the plurality of alternately stacked layers constituting the multi-layer film is controlled (by the control means). The one layer has a higher refractive index and is positioned near the uppermost surface remotest from the base. It has been found by the present inventors that, of the plurality of alternately stacked layers, one layer having a higher refractive index and being positioned near the uppermost surface remotest from the base exerts a large effect on the optical characteristic of the optical component. As a result, by controlling the thickness of such a layer (by the control means), it is possible to produce an optical component having a good optical characteristic.

BRIEF DESCRIPTION OF THE DRAWINGS

Fig. 1 is a plan view showing a configuration example of an optical thin layer forming apparatus as a preferred embodiment of the present invention;

Fig. 2 is a block diagram showing a configuration example of an optical monitor shown in Fig. 2;

Fig. 3 is a sectional view showing one example of a cross-sectional structure of an optical component formed by the optical thin layer forming apparatus;

Figs. 4A to 11B are characteristic diagrams showing examples of transmittance distributions relative to wavelengths of light;

Fig. 12 is a diagram showing an actual change in mean transmittance in the case of gradually increasing the thickness of an optical thin layer by using the optical monitor;

Fig. 13 is a diagram showing one example of a difference in final transmittance distribution between an optical component in which the thickness adjustment by using the optical monitor is performed and an optical component in which the thickness adjustment by using the optical component is not performed;

Fig. 14 is a characteristic diagram showing one

example of a transmittance distribution relative to wavelengths of light for an optical component formed by a related art optical thin layer producing method; and

Fig. 15 is a characteristic diagram showing one example of a transmittance distribution relative to wavelengths of light for an optical component formed by the related art optical thin layer producing method.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENT

Hereinafter, a preferred embodiment of the present invention will be described with reference to the accompanying drawings.

Fig. 1 is a plan view showing a configuration example of an optical thin layer forming apparatus 1 as a preferred embodiment of the present invention.

The optical thin layer forming apparatus or optical component producing apparatus 1 is used for forming optical thin layers on a base such as a high polymer film. Specific examples of the optical components produced by the apparatus 1 may include an dichroic mirror used for a projection television, an UV-IR filter (ultraviolet rays and infrared rays cutting filter), and a band filter. The following description will be made by using a dichroic mirror as an optical component.

The optical thin layer forming apparatus 1 has a feed roll 4 (film formation means), a winding roll 6 (film formation means), guide rolls 5a, 5b, 5c, 5d, 5e, and 5f (film formation means), a plasma electrode 8 (film formation means), evaporation sources 7a and 7b (film formation means), and an optical monitor 10 (measurement means). A gas lead valve 9 and an evacuation system 2 are connected to the apparatus 1. Preferably, the apparatus 1 has removal means 27.

A running system (film formation means) for running, at a constant speed, a base 3a from the feed roll 4 to the winding roll 6 by way of the guide rolls 5a, 5b, 5c, 5d, and 5f. The plasma electrode 8, which is used for preparation such as degassing of the base 3a, is opposed to a portion, disposed between the guide rolls 5a and 5b, of the base 3a. The evaporation sources 7a and 7b, each of which is configured typically as a sputtering system, are disposed with their targets opposed to the guide roll 5d. The target is made from Si, Nb or the like as an optical thin layer material.

The gas lead valve 9, which is connected to the apparatus 1, is used for adjusting, upon sputtering, the flow rate of a reaction gas to be supplied in the apparatus 1 such as argon (Ar) gas or oxygen gas. While

not shown, the guide roll 5d has a cooled structure for preventing the temperature rise of the base 3a upon film formation.

The optical monitor 10 is used for measuring an optical characteristic of an optical component obtained by forming optical thin layers on the surface of the base 3a. The optical characteristic to be measured is represented by a light transmittance, preferably, a mean light transmittance of an optical component. Since the apparatus 1 has the optical monitor 10, it can accurately measure a mean light transmittance of an optical component obtained by forming a multi-layer film having a plurality of optical thin layers.

The removal means 27, which is operated by a control unit 25, is used for removing an excess layer portion formed in a period of time from a time point at which the increase/decrease of a mean light transmittance measured by the optical monitor 10 is stopped to a time point at which the mean light transmittance is changed to be decreased. With this configuration, since the apparatus 1 can remove the above excess layer portion, the layer thickness can be finely adjusted. Accordingly, the apparatus 1 can produce an optical component having a good optical characteristic.

Fig. 2 is a block diagram showing a configuration example of the optical monitor 10 shown in Fig. 1.

The optical monitor 10 includes an optical source 10c, an optical head 10g, and a spectroscope 10d. The optical monitor 10 preferably further includes a switch 10f. These devices are connected to each other via optical communication lines such as optical fibers except for a signal line for connecting the spectroscope 10d to the control unit 25.

The optical head 10g has a light emitting unit 12 and a light receiving unit 13. The light emitting unit 12 is a light source enabling continuous emission of light having a wavelength of 450 to 700 nm, that is, a light source having a continuous spectrum of 450 to 700 nm in wavelength. The light emitting unit 12 is configured as an LED (Light Emitting Device). The light receiving unit 13 is configured as a photodiode for detecting a continuous spectrum of 450 to 700 nm in wavelength. The light emitting unit 12 and the light receiving unit 13 are opposed to each other with the running base 3a put therebetween. The light emitting unit 12 is connected to the light source 10c. The light source 10c is, in principle, supplies a specific quality of light. An optical communication line 10b extending from the switch

10f is connected to a mid point of the communication line between the light emitting unit 12 and the light source 10c.

The light receiving unit 13 is connected to the spectroscope 10d, and preferably, the switch 10f to which the optical communication line 10b is connected is provided between the light receiving unit 13 and the spectroscope 10d. The light receiving unit 13 receives a light component, passing through the base 3a, of light emitted from the light emitting unit 12. The switch 10f detects a variation in quality of light emitted from the light source 10c by way of the optical communication line 10b. Accordingly, if the quality of light emitted from the light source 10c varies, the spectroscope 10d can detect a rate of the quality of light received by the light receiving unit 13 to the quality of light emitted from the light emitting unit 12 in consideration of the increased/decreased quality of light.

The spectroscope 10d is connected to the control unit 25 and is controlled by the control unit 25. The spectroscope 10d can accurately calculate a rate (transmittance) of a light component, passing through the base 3a, of light emitted from the light emitting unit 12 by the function of the switch 10f. The transmittance thus

calculated is supplied to the control unit 25.

The control unit 25 controls a thickness of a portion of the multi-layer film to be formed on the optical component on the basis of the transmittance (or mean transmittance) thus supplied thereto. Of the multi-layer film to be formed on the optical component, one film layer (tuning layer 32 in Fig. 3) having a higher refractive index and being positioned near the uppermost surface remotest from the base is controlled by the control unit 25. The tuning layer 32, which is a higher refractive index layer of the multi-layer film composed of layers different in refractive index to be described later, exerts a large effect on the optical characteristic of the optical component. As a result, by controlling the thickness of the tuning layer 32 by means of the control unit 25, it is possible to produce an optical component having a good optical characteristic.

Fig. 3 is a sectional view showing one example of a cross-sectional structure of an optical component formed by the optical thin layer forming apparatus 1 shown in Fig. 1.

An optical component includes the base 3a, a hard coat layer 3b, a lower refractive index layer 3c', and a multi-layer film 30, which are arranged in this order

from bottom to top. The multi-layer film 30 is obtained by forming lower refractive index layers 3c and higher refractive index layers 3d one by one in such a manner that the layers 3c and 3d are alternately stacked. To be more specific, the optical component is obtained by repeating alternative stacking of the lower refractive index layers 3a and higher refractive index layers 3d by 21 times on the base 3a covered with the hard coat layer 3b via the lower refractive index layer 3c'.

The determination of the position of the tuning layer 32 in the multi-layer film 30 will be described below.

Figs. 4A to 11B are characteristic diagrams showing examples of transmittance distributions relative to wavelengths of light. In these figures, the abscissa indicates the wavelength (nm) and the ordinate indicates the transmittance (%). In addition, values described beside curves showing optical characteristics in each of Figs. 4A to 11B designate thicknesses of the tuning layers 32.

Fig. 4A shows optical characteristics for light incident on the base 3a in the vertical direction, which are examples of optical characteristics showing the results outputted from the optical monitor 10, and Fig.

4B shows optical characteristics for light incident on the base 3a at an angle of 45° with respect to the vertical direction, which are examples of optical characteristics of optical components (dichroic mirrors in this embodiment).

Figs. 5A, 6A, 7A, 8A, 9A, 10A and 11A are each similar to Fig. 4A; and Figs. 5B, 6B, 7B, 8B, 9B, 10B and 11B are each similar to Fig. 4B.

Figs. 4A to Fig. 7B show the transmittance characteristics relative to wavelengths of light for an optical component including the multi-layer film 30 obtained by stacking the lower refractive index layers 3c, higher refractive index layers 3d, lower refractive index layers 3c, . . . , higher refractive index layers 3d, and lower refractive index layers 3c in this order from bottom to top. The tuning layer 32 is set at the 18th layer in Figs. 4A and 4B, the 19th layer in Figs. 5A and 5B, the 20th layer in Figs. 6A and 6B, and the 21st layer in Figs. 7A and 7B.

From the optical characteristics of the dichroic mirror, it becomes apparent that depending on a change in layer thickness, the optical characteristic of the higher refractive index layer 3d is changed larger than the optical characteristic of the lower refractive index

layer 3c does. Further, as the results outputted from the optical monitor 10 shown in Figs. 4A, 5A, 6A and 7A, in the case where the tuning layer 32 is taken as the 20th higher refractive index layer 3d, the transmittance becomes the peak value at the ideal thickness in the transmission wavelength band (450 to 550 nm); while in the case where the tuning layer 32 is taken as the 18th high refractive index layer 3d, the transmittance does not become the peak value at the ideal thickness in the transmission wavelength band (450 to 550 nm).

Figs. 8A to Fig. 11B show the transmittance characteristics relative to wavelengths of light for an optical component including the multi-layer film 30 obtained by stacking the higher refractive index layers 3d, lower refractive index layers 3c, higher refractive index layers 3d, . . . , lower refractive index layers 3c and higher refractive index layers 3d in this order from bottom to top. The tuning layer 32 is set at the 18th layer in Figs. 8A and 8B, the 19th layer in Figs. 9A and 9B, the 20th layer in Figs. 10A and 10B, and the 21st layer in Figs. 11A and 11B.

From the optical characteristics of the dichroic mirror, it becomes apparent that depending on a change in layer thickness, the optical characteristic of the higher

refractive index layer 3d is changed larger than that of the lower refractive index layer 3c. Further, as the results outputted from the optical monitor 10 shown in Figs. 8A, 9A, 10A and 11A, in the case where the tuning layer 32 is taken as the 21st higher refractive index layer 3d, the transmittance becomes the peak value at the ideal thickness in the transmission wavelength band (450 to 550 nm); while in the case where the tuning layer 32 is taken as the 19th high refractive index layer 3d, the transmittance does not become the peak value at the ideal thickness in the transmission wavelength band (450 to 550 nm).

As is apparent from the above-described simulation, it may be desirable that, of the plurality of alternately stacked layers constituting the multi-layer film 30 formed on the optical component, the higher refractive index film 3d positioned near the uppermost surface remotest from the base 3a be set as the tuning layer 32.

Next, one example of a method of producing an optical component using the optical component producing apparatus will be described with reference to Figs. 1 to 3, and Figs. 12 and 13.

In the optical thin layer forming apparatus 1, the base 3a having a thickness of 188 μm , made from

polyethylene naphthalate, is set on the feed roll 4 to be wound around the winding roll 6 by way of the guide rolls 5a, 5b, 5c, 5d, 5e, and 5f.

An SiO_x (x is a positive number of 2 or less) is formed on the base 3a by sputtering the evaporation source 7a having an Si target while adjusting a flow rate of each of Ar gas and oxygen gas. Subsequently, 21 optical thin layers made from SiO_2 and Nb_2O_5 are formed one by one to satisfy a predetermined optically designed configuration by alternately sputtering the evaporation source 7b having an Nb target and the evaporation source 7a having the Si target while adjusting a flow rate of each of Ar gas and oxygen gas. In addition, the SiO_x layer is taken as one of the SiO_2 layers of the above 21 layers.

Upon formation of the optical thin layers, to reduce a stress applied to the optical thin layers, the flow rate of each of Ar gas and oxygen gas for sputtering is adjusted by the gas lead valve 9 to change the sputtering pressure. For example, while the usual sputtering pressure is about 0.3 Pa, the sputtering pressure used in this embodiment is set at about 1.6 Pa, to reduce the entire internal stress of the optical thin layers while adjusting the balance in stress between SiO_2

and Nb_2O_5 , thereby reducing a curling of the film-like base 3a.

With respect to the base 3a, previously, a hard coat layer is formed on the surface on which optical thin layers are to be formed, and an adhesive layer is formed on the opposed surface to the optical thin layer formation surface and a protective film is formed on the adhesive layer. Since the base 3a made from polyethylene naphthalate has a high heat resistance, that is, a high resistance against thermal deformation, optical thin layers can be uniformly formed on the base 3a. For example, polyethylene naphthalate having a glass transition point of 110°C is superior in heat resistance to polyethylene terephthalate having a glass transition point of 69°C .

A glass plate having a width of 5 cm, a length of 8.75 cm, and a thickness of 1 mm is prepared as a transparent member. The base 3a, on which the optical thin layers have been formed, is laminated on the transparent member via an adhesive, and is then cut into a size matched to that of the glass plate. In this way, an optical component applicable to a dichroic mirror used for typically a projection television is finished. In addition, a protective film formed on an adhesive layer

may be used as the transparent member.

As described above, the optical monitor 10 is essential for stably producing an optical component (optical filter) having a high quality.

Fig. 12 is a diagram showing one example of simulation of a change in mean transmittance in the case of gradually increasing the thickness of an optical thin layer by using the optical monitor, and Fig. 13 is a diagram showing one example of a difference in final transmittance distribution between an optical component in which the thickness adjustment by using the optical monitor is performed and an optical component in which the thickness adjustment by using the optical monitor is performed.

Fig. 12 shows a change in mean transmittance in the case of changing the thickness of the tuning layer 32 by about $\pm 20 \mu\text{m}$ in the case where light is made incident on the base in the vertical direction. The ideal thickness of the tuning layer is typically 94.76 nm. The mean transmittance of the tuning layer 32 is increased as the thickness thereof is gradually increased from 74.76 nm, reaching the peak value when the thickness of the layer 32 is increased to about 94.76 nm, and is changed to be decreased as the thickness of the layer 32 is further

increased. Further, as shown in Fig. 13, the mean transmittance in a transmission wavelength band (450 to 550 nm) of the optical component in which the thickness adjustment by using the optical monitor 10 is performed is about 7% higher than that of the optical component in which the thickness adjustment by using the optical monitor 10 is not performed. Accordingly, it is possible to produce an optical component having a high quality by using the optical monitor 10.

According to this embodiment, it is possible to easily, stably produce an optical component having a good optical characteristic.

While the preferred embodiment has been described using the specific terms, such description is for illustrative purposes only, and it is to be understood that changes and variations may be made without departing from the spirit or scope of the following claims.

CLAIMS:

1. An optical component producing apparatus for forming a multi-layer film, which is composed of alternately stacked layers different in optical characteristic, on a base, said apparatus comprising:

film formation means for forming said multi-layer film on said base;

measurement means for measuring an optical characteristic of said optical component obtained by forming said multi-layer film on said base; and

control means for controlling a thickness of a portion of said multi-layer film to be formed by said film formation means on the basis of the measured optical characteristic of said optical component.

2. An optical component producing apparatus according to claim 1, wherein said measurement means measures a transmittance of said optical component; and

said control means terminates the film formation by said film formation means at said portion of said multi-layer film when said measured transmittance of said optical component is changed to be decreased.

3. An optical component producing apparatus according to claim 2, further comprising removal means for removing the layer portion formed during a period of

time from a time point when the increase/decrease of the measured transmittance of said optical component is stopped to a time point when the measured transmittance is changed to be decreased.

4. An optical component producing apparatus according to claim 1, wherein said control means controls a thickness of one layer of said plurality of alternately stacked layers, said one layer having a higher refractive index and being positioned near the uppermost surface remotest from said base.

5. An optical component producing method for forming a multi-layer film, which is composed of alternately stacked layers different in optical characteristic, on a base, said method comprising:

measuring an optical characteristic of said optical component obtained by forming said multi-layer film on said base; and

controlling, on the basis of the measured optical characteristic of said optical component, a thickness of a portion of said multi-layer film to be formed on said base.

6. An optical component producing method according to claim 5, wherein said measurement step comprises the step of measuring a transmittance of said optical

component; and

said control step comprises the step of terminating the film formation at said portion of said multi-layer film when said measured transmittance of said optical component is changed to be decreased.

7. An optical component producing method according to claim 6, further comprising removal step of removing a layer portion formed during a period of time from a time point when the increase/decrease of the measured mean light transmittance of said optical component is stopped to a time point when the measured mean light transmittance is changed to be decreased.

8. An optical component producing method according to claim 5, wherein said control steps comprises the step of controlling a thickness of one layer of said plurality of alternately stacked layers, said one layer having a higher refractive index and being positioned near the uppermost surface remotest from said base.

ABSTRACT OF THE DISCLOSURE

Disclosed is an optical component producing apparatus for forming a multi-layer film, which is composed of alternately stacked layers different in optical characteristic, on a base. The apparatus includes film formation means for forming the multi-layer film on the base; measurement means for measuring an optical characteristic of the optical component obtained by forming the multi-layer film on the base; and control means for controlling a thickness of a portion of the multi-layer film formed by the film formation means on the basis of the measured optical characteristic of the optical component.

6,000,000,000

FIG. 1




FIG. 2




FIG. 3




FIG. 4A




FIG. 4B




FIG.5A




FIG.5B




FIG. 6A




FIG. 6B




FIG. 7A




FIG. 7B




FIG. 8A




FIG. 8B




FIG. 9A




FIG. 9B




FIG. 10A




FIG. 10B




FIG. IIA




FIG. IIB




FIG. 12




FIG. 14





FIG. 15



DECLARATION AND POWER OF ATTORNEY FOR PATENT APPLICATION

特許出願宣言書及び委任状

Japanese Language Declaration

日本語宣言書

下記の氏名の発明者として、私は以下の通り宣言します。

私の住所、私書箱、国籍は下記の私の氏名の後に記載された通りです。

下記の名称の発明に関して請求範囲に記載され、特許出願している発明内容について、私が最初かつ唯一の発明者（下記の氏名が一つの場合）もしくは最初かつ共同発明者であると（下記の名称が複数の場合）信じています。

As a below named inventor, I hereby declare that:

My residence, post office address and citizenship are as stated next to my name,

I believe I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled

“INSPECTION APPARATUS”

上記発明の明細書（下記の欄でx印がついていない場合は、本書に添付）は、

the specification of which is attached hereto unless the following box is checked:

☐ 月 日に提出され、米国出願番号または特許協定条約
国際出願番号を _____ とし、
(該当する場合) _____ に訂正されました。

☐ was filed on _____ as United States
Application Number _____ and was amended on
_____ (if applicable)

私は、特許請求範囲を含む上記訂正後の明細書を検討し、
内容を理解していることをここに表明します。

I hereby state that I have reviewed and understand
the contents of the above identified specification,
including the claims, as amended by any amendment
referred to above.

私は、連邦規則典第37編第1条56項に定義されると
おり、特許資格の有無について重要な情報を開示する義務が
あることを認めます。

I acknowledge the duty to disclose information which
is material to patentability as defined in Title 37, Code
of Federal Regulations, Section 1.56.

私は、米国法典第35編119条(a)-(d)項又は365条(b)項に基づき下記の、米国外の国の少なくとも一ヶ国を指定している特許協力条約365(a)項に基づき国際出願、又は外国での特許出願もしくは発明者証の出願についての外国優先権をここに主張するとともに、優先権を主張している、本出願の前に出願された特許または発明者証の外国出願を以下に、枠内をマークすることで、示しています。

Prior Foreign Application(s)

外国での先行出願
P11-294406 Japan October 15, 1999

(Number) (番号)	(Country) (国名)	(Day Month Year Filed) (出願年月日)
------------------	-------------------	-----------------------------------

(Number) (番号)	(Country) (国名)	(Day Month Year Filed) (出願年月日)
------------------	-------------------	-----------------------------------

私は、第35編米国法典119条(e)項に基づいて下記の米
国特許出願規定に記載された権利をここに主張いたします。

(Application No.) (出願番号)	(Filing Date) (出願日)
-----------------------------	------------------------

私は、下記の米国法典第35編120条に基づいて下記の米
国特許出願に記載された権利、又は米国を指定している特許
協力条約365条(c)に基づき権利をここに主張します。また、本出願の各請求範囲の内容が米国法典第35編112条
第1項又は特許協力条約で規定された方法で先行する米国特
許出願に開示されていない限り、その先行米国出願書提出日
以降で本出願書の日本国内または特許協力条約国際提出日ま
での期間中に入手された、連邦規則法典第37編1条56項
で定義された特許資格の有無に関する重要な情報について開
示義務があることを認識しています。

I hereby claim foreign priority under Title 35, United States Code, Section 119(a)-(d) or 365(b) of any foreign application(s) for patent or inventor's certificate or 365(a) of any PCT international application which designated at least one country other than the United States, listed below and have also identified below, by checking the box, any foreign application for patent or inventor's certificate or PCT International application having a filing date before that of the application on which priority is claimed:

Priority Not Claimed

優先権主張なし

(Number)	(Country)	(Day Month Year Filed)
----------	-----------	------------------------

(Number)	(Country)	(Day Month Year Filed)
----------	-----------	------------------------

I hereby claim the benefit under Title 35, United States Code, Section 119(e) of any United States provisional application(s) listed below.

(Application No.) (出願番号)	(Filing Date) (出願日)
-----------------------------	------------------------

I hereby claim the benefit under Title 35, United States Code, Section 120 of any United States application(s) or 365(c) of an PCT International application designating the United States, listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States or PCT International application in the manner provided by the first paragraph of Title 35, United States Code, Section 112, I acknowledge the duty to disclose information which is material to patentability as defined in Title 37, Code of Federal Regulations, Section 1.56 which became available between the filing date of the prior application and the national or PCT International filing date of this application.

(Application No.)
(出願番号)

(Filing Date)
(出願日)

(Status: patented, pending, abandoned)
(現況: 特許許可済、係属中、放棄済)

Application No.)
(出願番号)

(Filing Date)
(出願日)

(Status: patented, pending, abandoned)
(現況: 特許許可済、係属中、放棄済)

私は、私自身の知識に基づいて本宣言書中で私が行なう表明が真実であり、かつ私の入手した情報と私の信じているところに基づき表明が全て真実であると信じていること、さらに故意になされた虚偽の表明及びそれと同等の行為は米国法典第18編第1001条に基づき、罰金または拘禁、もしくはその両方により処罰されること、そしてそのような故意による虚偽の声明を行なえば、出願した、又は既に許可された特許の有効性が失われることを認識し、よってここに上記のごとく宣誓を致します。

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

委任状: 私は下記の発明者として、本出願に関する一切の手続きを米特許商標局に対して遂行する弁理士または代理人として、下記の者を指名いたします。(弁理士、または代理人の氏名及び登録番号を明記のこと)

POWER OF ATTORNEY: As a named inventor, I hereby appoint the following attorney(s) and/or agent(s) to prosecute this application and transact all business in the Patent and Trademark Office connected therewith. (list name and registration number)

David R. Metzger (Reg. No. 32,919), Joseph A. Mahoney (Reg. No. 38,956), Howard B. Rockman (Reg. No. 22,190), Jordan A. Sigale, (Reg. No. 39,028), Michael A. Molano (Reg. No. 39,777), Michael L. Kiklis (Reg. No. 38,939), Janielle D. Strode (Reg. No. 34,738), Kevin W. Guynn (Reg. No. 29,972), Jennifer Hammond (Reg. No. 41,814), Lana Knedlik (Reg. No. 42,748), John F. Griffith (Reg. No. 44,137), Marina Saito (Reg. No. 42,121), Alison P. Schwartz (Reg. No. 43,863), Christopher P. Rauch (Reg. No. 45,034), Francisco Rubio-Campos (Reg. No. 45,358), Brian J. Gill (Reg. No. 46,727) and Shashank S. Upadbye, all members of the firm of Sonnenschein, Nath & Rosenthal

Send Correspondence to:

書類送付先

David R. Metzger
Sonnenschein Nath & Rosenthal
P.O. Box #061080
Wacker Drive Station
Chicago, Illinois 60606-1080

直接電話連絡先: (名前及び電話番号)

Direct Telephone Calls to: (name and telephone number)

312/876-2578

唯一または第一発明者名	Full name of sole or first inventor: KAZUHITO SHIMODA
発明者の署名 日付	Inventor's signature Date
住所	Residence Kanagawa Japan
国籍	Citizenship Japan
私書箱	Post Office Address c/o Sony Corporation 7-35, Kitashinagawa 6-chome Shinagawa-ku, Tokyo 141, Japan

(第三以降の共同発明者についても同様に記載し、署名をする)

第二共同発明者	Full name of second joint inventor, if any: JUNICHI OHSAKO
発明者の署名 日付	Inventor's signature Date
住所	Residence Tokyo, Japan
国籍	Citizenship Japan
私書箱	Post Office Address c/o Sony Corporation 7-35, Kitashinagawa 6-chome Shinagawa-ku, Tokyo 141, Japan
第三共同発明者	Full name of third joint inventor, if any:
発明者の署名 日付	Inventor's signature Date
住所	Residence
国籍	Citizenship
私書箱	Post Office Address

Japanese Language Declaration

(日本語宣言書)